

US AGM 24 SPECIFICATIONS																				
BCI												Standard		MINUTES	MINUTES	MINUTES				wet
Group	Model	1-hr	2-hr	5-hr	6-hr	10-hr	20-hr	48-hr	72-hr	100-hr	Voltage	Terminal		@	@	@	Length		Height	Weight
Size		Rate	Rate	Rate	Rate	Rate	Rate	Rate	Rate	Rate		Туре	(20 HR. RATE)	75 AMPS	56 AMPS	25 AMPS	10.24"	6.61"	8.43"	Lbs (kg)
24	US AGM 24	58	67	82	83	85	90	92	92	93	12	T6-A	90	43	65	175	(260)	(168)	(214)	52 (23.5)

CHARGING INSTRUCTIONS:

Nominal Charge Current (amps)	9						
Max Charge Current (w/ temp. compensation)	18						
Max Charge Voltage (temp. compensated)	14.9						
Float/Maintenance Voltage (temp. compensated)	13.8						
Temperature Compensation	-4 mV/cell/°C (-2 mV/cell/°F)						
For automatic chargers, use settings compatible with AGM batteries							

Do not charge at temperature corrected voltages above 15 volts (2.5 volts/cell). Use of a voltage controlled charger is a requirement for warranty coverage. For best cycle life, limit discharge to less than 50% of the battery's 20 hour capacity.

Deep cycle batteries need to be equalized periodically. Equalizing is an extended, low current charge performed after the normal charge cycle. This extra charge helps keep all cells in balance. Actively used batteries should be equalized once per month. Manually timed chargers should have the charge time extended approximately 3 hours. Automatically controlled chargers should be unplugged and reconnected after completing a charge.

All of our sealed AGM batteries are specifically manufactured for U.S. Battery under our guidelines assuring our customers they are being provided the highest quality AGM batteries available.

For more information or questions, please visit WWW.USBATTERY.COM













1675 Sampson Avenue Corona, CA 92879 (800) 695-0945



T6-A Terminal





U.S. Battery Operating Temperature Guidelines

For charging, we recommend staying within 0°F to 120° F (-18 to 49° C) to avoid charging frozen batteries at low temperature or going into thermal runaway at high temperature.

For discharging, we recommend -20°F to 120°F (-29 to 49°C).

Batteries discharged at temperatures below 32°F (0°C) should be recharged immediately to avoid freezing.

Batteries discharged at temperatures above 120°F (49°C) should be allowed to cool before recharging.

Extreme temperatures can substantially affect battery performance and charging. Cold reduces battery capacity and retards charging. Heat increases water usage and can result in overcharging. Very high temperatures can cause "thermal run-away" which may lead to an explosion or fire. If extreme temperature is an unavoidable part of an application, consult a battery/charger specialist about ways to deal with the problem.

Data references within this publication are nominal and should not be considered or construed as maximum or minimum values for specifications or for final design. Data for this product type and model may vary from what is shown in this publication, and U.S. Battery Mfg, Co. makes No warranties, expressed or implied based on the data within this publication.

©2024 U.S. Battery Mfg., Co. All rights reserved. U.S. Battery is not liable for damages that may occur from any information provided in or omitted from this publication, under any circumstances. U.S. Battery Mfg., Co. reserves the right to make changes or adjustments to this publication at any time without notices or obligations.

1895 Tobacco Road Augusta, GA 30906 (800) 522-0945 717 North Belair Rd. Evans, GA 30809 (888) 811-0945